

January 26, 2010

To whom it may concern:

Rogers Corporation, with aid of experts in the field, has given careful consideration to how EU regulation REACH (Registration, Evaluation, Authorisation and Restriction of Chemicals) has an impact on our product line of Power Distribution Systems. The conclusion is that our **RO-LINX®** Busbars, both manufactured in Europe and in China, are defined as articles in this legislation.

Further, none of our typical^(*) busbars contain any of the following Substances of Very High Concern (SVHC), as updated on the ECHA website on January 13, 2010):

Substance name	EC N°	CAS N°	Publication
2,4-Dinitrotoluene	204-450-0	121-14-2	13/01/2010
4,4'- Diaminodiphenylmethane	202-974-4		28/10/2008
5-tert-butyl-2,4,6-trinitro-m-xylene (musk xylene)	201-329-4		28/10/2008
Alkanes, C10-13, chloro (Short Chain Chlorinated Paraffins)	287-476-5		28/10/2008
Aluminosilicate Refractory Ceramic Fibres <i>Aluminosilicate Refractory Ceramic Fibres are fibres covered by index number 650-017-00-8 in Annex VI, part 3, table 3.2 of Regulation (EC) No 1272/2008, and fulfil the two following conditions:</i> <i>a) Al₂O₃ and SiO₂ are present within the following concentration ranges:</i> <i>• Al₂O₃: 43.5 – 47 % w/w, and SiO₂: 49.5 – 53.5 % w/w, or</i> <i>• Al₂O₃: 45.5 – 50.5 % w/w, and SiO₂: 48.5 – 54 % w/w,</i> <i>b) fibres have a length weighted geometric mean diameter less two standard geometric errors of 6 or less micrometers (µm).</i>	-	-	13/01/2010
Anthracene	204-371-1		28/10/2008
Anthracene oil	292-602-7	90640-80-5	13/01/2010
Anthracene oil, anthracene paste	292-603-2	90640-81-6	13/01/2010
Anthracene oil, anthracene paste, anthracene fraction	295-275-9	91995-15-2	13/01/2010
Anthracene oil, anthracene paste, distn. lights	295-278-5	91995-17-4	13/01/2010
Anthracene oil, anthracene-low	292-604-8	90640-82-7	13/01/2010
Benzyl butyl phthalate	201-622-7		28/10/2008
Bis (2-ethylhexyl)phthalate (DEHP)	204-211-0		28/10/2008
Bis(tributyltin)oxide	200-268-0		28/10/2008
Cobalt dichloride	231-589-4		28/10/2008
Diarsenic pentaoxide	215-116-9		28/10/2008
Diarsenic trioxide	215-481-4		28/10/2008
Dibutyl phthalate	201-557-4		28/10/2008
Diisobutyl phthalate	201-553-2	84-69-5	13/01/2010

Substance name	EC N°	CAS N°	Publication
Hexabromocyclododecane (HBCDD) and all major diastereoisomers identified: - Alpha-hexabromocyclododecane - Beta-hexabromocyclododecane - Gamma-hexabromocyclododecane	247-148-4 and 221- 695-9	134237- 50-6 134237- 51-7 134237- 52-8	28/10/2008
Lead chromate	231-846-0	7758-97-6	13/01/2010
Lead chromate molybdate sulphate red (C.I. Pigment Red 104)	235-759-9	12656-85- 8	13/01/2010
Lead hydrogen arsenate	232-064-2		28/10/2008
Lead sulfochromate yellow (C.I. Pigment Yellow 34)	215-693-7	1344-37-2	13/01/2010
Pitch, coal tar, high temp.	266-028-2	65996-93- 2	13/01/2010
Sodium dichromate	234-190-3	7789-12-0 and 10588- 01-9	28/10/2008
Triethyl arsenate	427-700-2		28/10/2008
tris(2-chloroethyl)phosphate	204-118-5	115-96-8	13/01/2010
Zirconia Aluminosilicate, Refractory Ceramic Fibres <i>Zirconia Aluminosilicate Refractory Ceramic Fibres are fibres covered by index number 650-017-00-8 in Annex VI, part 3, table 3.2 of Regulation (EC) No 1272/2008, and fulfil the two following conditions:</i> <i>a) Al₂O₃, SiO₂ and ZrO₂ are present within the following concentration ranges:</i> <i>• Al₂O₃: 35 – 36 % w/w, and</i> <i>• SiO₂: 47.5 – 50 % w/w, and</i> <i>• ZrO₂: 15 - 17 % w/w,</i> <i>b) fibres have a length weighted geometric mean diameter less two standard geometric errors of 6 or less micrometers (µm).</i>	-	-	13/01/2010

If you need any further assistance concerning this, please do not hesitate to contact your assigned customer service person,

Sincerely,



Marc Beulque
General Manager
Rogers Corporation
Power Distribution Systems

(*): busbars with custom made connectors, cables and/or other components are considered non-typical.